

SK-77

TOTAL TRANSFER SECURITY TAPE FOR STRETCH FILM

PRODUCT DESCRIPTION

Traces of prints or patterns are totally transferred to substrates when the tape is removed. Excellent tamper evident performance.

ADDITIONAL INFORMATION

Perforation & sequential numbering are available.

APPLICATION

Suitable to seal paper packages, cardboard boxes and pallet wrap stretch films.

TECHNICAL DATA

90°C Peel Adhesive for VOID

0.20-0.98N/2,5cm - PSTC-1

Total Thickness

0.075-0.085mm

Initial Tack

< 10cm PSTC-6 #14 ball

Holding power

1.0kg/2,5cm x 2,5cm: >24 hrs - PSTC-7

STANDARD SIZE

Width: 40mm, 48mm, 50mm, 75mm

Length: 50m~500m

COLOR

Red, blue, brown, orange, yellow, green, white and purple.

CARRIER:

PET

VOID TEMPERATURE

-40°C ~ +40°C

RECOMMENDED OPERATING TEMPERATURE

+10°C ~ +35°C

RELATIVE HUMIDITY

55% +/-10%

VOID MESSAGE

Standard VOID print;
customisable message upon request

ADDITIONAL PRINTING

Product is suitable to be top printed with own logo or text

SHELF LIFE

1 year under normal condition. Avoid exposing to high humidity and direct sunlight.

HOW TO APPLY

When applying the tape the surfaces to be bonded should be dry, dust & grease free and thoroughly clean. Avoid touching the exposed adhesive surface of the tape as this impairs the performance. The adhesive used on these tapes are pressure sensitive, so always ensure sufficient pressure is applied to the tape evenly over the whole surface to ensure the best bonding results.

All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller or Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.

Remark

(1) Test environment: Lab temperature 23 ± 5°C and humidity 55 ± 10% RH. (2) Avoid being exposed to high temperature, high humidity and sunlight for preserving. (3) Shelf life: 1 year under normal condition. (4) Testing before using to avoid the glue being affected from the unstable substance. (5) Above data is based on Seal King lab test results and for reference only. The actual reading is subject to users' application.